

General information

Diameter	1.75 mm
Net filament weight	1 kg
Spool weight	164 g
Spool size	200 mm (OD) x 67 mm (W)
Spool material	Polycarbonate (drying up to 120°C)

Recommended printing settings

Drying before printing	6 h @ 80°C
Nozzle Temperature	240 - 280 °C
Bed Temperature	80 - 100 °C
Chamber Temperature	30 - 80 °C
Annealing after printing	Not required

Physical and thermal properties

	Testing standard	Typical value
Density	ISO 1183	1.08 g/cm ³
Heat Deflection Temperature	ISO 75 - 0.45 MPa	95 °C (annealed)
Continuous Use Temperature	IEC 60216	130 °C

Mechanical properties

	Testing standard	Typical value
Tensile strength (X-Y)	ISO 527	34 MPa
Elongation at break (X-Y)	ISO 527	2.8 %
Young's modulus (X-Y)	ISO 527	2.8 GPa

Disclaimer: The technical data provided in this datasheet is furnished without charge or obligation and accepted at the recipient's sole risk. This data should not be used to establish specifications limits or used alone as the basis of design. The data provided is not intended to substitute any testing that may be required to determine fitness for any specific use.